

PRODUCT SPECIFICATION SHEET

BELZONA 1151

FN10017



GENERAL INFORMATION

Product Description:

A two-component, semi-paste grade material based on a silicon-steel alloy blended within high molecular weight reactive polymers and oligomers. The system is designed for rebuilding shallow pitting in metal substrates up to 6mm deep. Ideally suited to be overcoated with **Belzona 1321** (Ceramic S-Metal). Also used as a high strength structural adhesive for bonding or for creation of irregular load bearing shims with good electrical insulation characteristics. For use in Original Equipment Manufacture or repair situations.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Centrifugal and turbine pumps
- Propellers
- Bow thrusters
- Heat exchangers, water box ends, division bars and tube sheets
- Butterfly and gate valves
- Kort nozzles
- Pipework

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 77°F (25°C) the usable life of mixed material is 30 minutes.

Cure Time

Allow to solidify for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

Volume Capacity

74.9 in³ (1227 cm³)/3kg unit
24.95 in³ (409 cm³)/kg

Base Component

Appearance Paste
Color Dark gray
Gel strength at 77°F (25°C) >150 g/cm HF
Density 2.7 - 2.9 g/cm³

Solidifier Component

Appearance Liquid
Color Blue
Density 1.0 - 1.1 g/cm³

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier) 10.8 : 1
Mixing Ratio by Volume (Base : Solidifier) 4 : 1
Mixed Form Semi-paste
Slump Resistance nil at 0.25 inch (6mm)
Mixed Density 2.39-2.49 g/cm³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, to grit blasted substrate with 3-4 mil (75-100 micron) profile, typical values will be:
Mild steel 2,800 psi (19.3 MPa)

CORROSION PROTECTION

Corrosion Resistance

Once fully cured, will show no visible signs of corrosion after 5,000 hours exposure in the ASTM B117 salt spray cabinet.

COMPRESSIVE PROPERTIES

Compressive Strength

When determined in accordance with ASTM D695 typical values will be:
13,790 psi (95.1 MPa)

HARDNESS

Shore D

When determined in accordance with ASTM D2240, typical values will be:
ambient cure 88

Barcol

When determined in accordance with ASTM D2583, will typically be:
ambient cure 86
post cure 91

PRODUCT SPECIFICATION SHEET

BELZONA 1151

FN10017



HEAT RESISTANCE

Heat Distortion Temperature (HDT)

Tested to ASTM D648 (264 psi fiber stress), typical values will be:
ambient cure 111°F (44°C)
post cure 189°F (87°C)

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 392°F (200°C).

For many applications the product is suitable down to -40°F (-40°C).

Wet Heat Resistance

In immersed conditions **Belzona 1151** should be overcoated with a suitable Belzona coating.

SHELF LIFE

Separate base and solidifier components shall have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1151 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

