

PRODUCT SPECIFICATION SHEET

BELZONA 1211

FN10019



GENERAL INFORMATION

Product Description:

A two component rapid curing paste grade system based on a silicon steel alloy blended with high molecular weight reactive polymers and oligomers. Developed for high speed emergency repairs, bonding and rebuilding.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Leaking pipes
- Stripped threads
- Bearing seats
- Ducts
- Leaking tanks
- Plastic/metal joints
- Broken insulators
- Scored hydraulic rams
- Holed casings

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 77°F (25°C) the usable life of mixed material is 4 minutes.

Cure Time

Cure times will vary depending on the ambient conditions and will be reduced for thicker sections and extended for thinner applications. Consult the Belzona IFU for specific details.

Volume Capacity

27.5 cu.in (450 cm³)/kg
13.75 cu.in (225 cm³)/ 500g unit.

Base Component

Appearance	Paste
Color	Dark gray
Gel strength at 77°F (25°C)	>150 g/cm HF
Density	2.70 - 2.90 g/cm ³

Solidifier Component

Appearance	Paste
Color	Light gray
Gel strength at 77°F (25°C)	250 g/cm HF
Density	1.57 - 1.63 g/cm ³

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier)	2 : 1
Mixing Ratio by Volume (Base : Solidifier)	1 : 1
Mixed Form	Paste
Peak Exotherm Temperature	185 - 212°F (85 - 100°C)
Time to Peak Exotherm	8 - 10 mins.
Slump Resistance	nil at 0.5 inch (12.5 mm)
Mixed Density	2.15 - 2.27g/cm ³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 1211

FN10019



ADHESION

Tensile Shear

The tensile shear adhesion to a grit blasted substrate with a 3 mil. (75 micron) profile, when tested to ASTM D1002 after 7 days cure at 77°F (25°C), is typically :

Mild Steel	2500 psi (17.2 MPa)
Aluminium	1800 psi (12.4 MPa)
Copper	2250 psi (15.5 MPa)
Brass	2500 psi (17.2 MPa)
Galvanized steel	2200 psi (15.2 MPa)
Cupronickel	2500 psi (17.2 MPa)
Stainless steel	2500 psi (17.2 MPa)
Formica	>500 psi (3.4 MPa)*
Polyester/Fiberglass	>700 psi (4.8 MPa)*

* Cohesive failure within substrate

Pull Off Adhesion

When tested in accordance with ASTM D 4541/ ISO 4624, the pull off strength from grit blasted steel will be typically:
1970 psi (13.6 MPa)

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate good resistance to a broad range of commonly found chemicals including hydro-carbons, mineral oils and lubricating oils

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart

COMPRESSIVE PROPERTIES

Compressive Strength

The compressive strength of the material, when tested to ASTM D695 after 7 days cure at 77°F (25°C), is typically 8200 psi (56.5 MPa).

CORROSION PROTECTION

Corrosion Resistance

Once fully cured, will demonstrate no visible signs of corrosion after 5,000 hours exposure in the ASTM B117 salt spray cabinet.

FLEXURAL PROPERTIES

Flexural Strength

The flexural strength, when tested to ASTM D790 after 7 days at 77°F (25°C), is typically 8200 psi (56.5 MPa).

HARDNESS

Shore D

When determined in accordance with ASTM D2240, typical value will be:
80

Barcol

When determined in accordance with ASTM D2583, typical value will be:
78

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

The heat distortion temperature of the material, when tested to ASTM D648 (264 psi fiber stress) after 7 days cure at 77°F (25°C), is typically 109°F (43°C).

Heat Resistance

For many typical applications, the product is thermally stable to 212°F (100°C) dry and 140°F (60°C) wet.

IMPACT RESISTANCE

Impact Strength

The impact strength (reverse notched) when tested to ASTM D256 is typically:
0.73 ft.lb./in., 40 J/m

SHRINKAGE

Shrinkage is typically nil when tested in accordance with DOD-C-24176A method 4.6.12.

THERMAL EXPANSION

Tested to ASTM E228 the coefficient of thermal expansion is typically 53.3 ppm/°C.

PRODUCT SPECIFICATION SHEET

BELZONA 1211

FN10019



WATER UPTAKE

When tested for 3 days at 77°F (25°C) water uptake is typically 2.2%.

SHELF LIFE

Separate base and solidifier components shall have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

APPROVALS/ACCEPTANCES

The material has received recognition from organizations worldwide including:

- U.S.D.A.
- ABS
- NATO
- GENERAL MOTORS
- TOYOTA
- CHRYSLER
- FORD
- RJB MINING
- LEAD SHEET ASSOCIATION

WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1211 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2013 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

