

PRODUCT SPECIFICATION SHEET

BELZONA 1251

FN10021



GENERAL INFORMATION

Product Description:

A single component heat activated paste grade system based on a silicon steel alloy blended with a heat activated resin. When cured, the material is durable and corrosion resistant.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is designed to be applied to hot surfaces 158 - 302°F (70 - 150°C), such as under insulation metalwork.

APPLICATION INFORMATION

Working Life

Cure will not commence until the product is heated, hence the working life of **Belzona 1251** is effectively unlimited.

Cure Time

The cure time of **Belzona 1251** is primarily dependent on the heat-cure temperature - consult the Belzona IFU for specific details. The minimum recommended cure temperature for **Belzona 1251** is 158°F (70°C).

N.B. Increased thickness (>1/8in. or 3mm) may require additional heating time.

Volume Capacity

24.6 in³ (403 cm³)/kg.

Mixed Properties

Appearance

Color

Gel strength at 77°F (25°C)

Density

Paste
Dark gray
>200 g/cm HF
2.4 - 2.5 g/cm³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 1251

FN10021



ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, typical values will be:

2000 psi (13.8 MPa) after cure at 158°F (70°C) applied onto clean, ground steel.

2200 psi (15.2 MPa) after cure at 212°F (100°C) applied onto clean, ground steel.

3200 psi (22.1 MPa) after cure at 248°F (120°C) applied onto clean, ground steel.

1200 psi (8.3 MPa) after cure at 212°F (100°C) applied onto rusty steel prepared to ISO 8501-1 St 2 (wire brushed)

2100 psi (14.5 MPa) after cure at 212°F (100°C) applied onto rusty steel prepared to ISO 8501-1 St 3 (manually abraded)

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate excellent resistance to many commonly found inorganic acids and alkalis at concentrations up to 20%. The material is also resistant to hydrocarbons, mineral oils, lubricating oils and many other commonly found chemicals.

COMPRESSIVE PROPERTIES

When tested in accordance with ASTM D695, typical values will be:

Compressive Strength

17,400 psi (120.0 MPa) after 7 days cure at 158°F (70°C)
14,000 psi (96.5 MPa) after 1 day cure at 212°F (100°C)
18,100 psi (124.8 MPa) after 7 days cure at 212°F (100°C)

CORROSION PROTECTION

Corrosion Resistance

Will show no visible signs of corrosion after 5,000 hours exposure in the ASTM B117 salt spray cabinet.

FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

Flexural Strength

8700 psi (60.0 MPa) after 7 days cure at 158°F (70°C)
7700 psi (53.1 MPa) after 1 day cure at 212°F (100°C)
9000 psi (62.1 MPa) after 7 days cure at 212°F (100°C)

HARDNESS

Shore D

When determined in accordance with ASTM D2240, typical value will be:

88 212°F/100°C cure

Barcol

When determined in accordance with ASTM D2583, typical value will be:

97 212°F/100°C cure

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

Tested in accordance with ASTM D648 (264 psi fiber stress), typical values obtained will be:

225°F (107°C) after 7 days cure at 158°F (70°C)
248°F (120°C) after 7 days cure at 212°F (100°C)

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 410°F (210°C).

IMPACT RESISTANCE

Impact Strength

The impact strength (un-notched) when tested to ASTM D256 is typically:

1.04 ft.lb./in., 56 J/m 212°F (100°C) cure

SHELF LIFE

Belzona 1251 will have a shelf life of at least 24 months when stored at 68°F (20°C). Refrigeration of this product will extend the shelf life.

PRODUCT SPECIFICATION SHEET

BELZONA 1251

FN10021



WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1251 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

