

PRODUCT SPECIFICATION SHEET

BELZONA 5891

FN10105



GENERAL INFORMATION

Product Description:

A two component, epoxy/amine system containing mineral and ceramic fillers. Provides excellent corrosion resistance when immersed in water/hydrocarbon mixtures up to 194°F(90°C). Applied by brush or heated airless spray. May also be applied by injection to create irregular shims.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Effluent tanks and channels
- Water boxes
- Separators
- Condensers
- Knock out drums
- Evaporators
- Condensate tanks
- Strippers and scrubbers

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 68°F (20°C) the usable life of mixed material is 45 minutes.

Coverage Rate

The **Belzona 5891** shall be applied to achieve a minimum thickness of 16 mils (400 microns). At this thickness the theoretical coverage rate is 27sq.ft. (2.5 m²)/litre.

Refer to the Instructions For Use for practical coverage rate guidelines.

Cure Time

Allow to cure for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

In certain instances it may be necessary to post cure material prior to putting into service where chemical contact is involved or service temperature is below 86°F (30°C).

Base Component

Appearance	Viscous liquid
Color	Grey
Density	1.75 - 1.79 g/cm ³

Solidifier Component

Appearance	Thin liquid
Color	Amber
Density	0.95 - 0.99 g/cm ³

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier)	13 : 1
Mixing Ratio by Volume (Base : Solidifier)	7.2 : 1
Density	1.65 - 1.69 g/cm ³
Time to peak exotherm	125-160 mins.
Peak exotherm temperature	122-149°F (50-65°C)
Viscosity	55-65 poise
Sag resistance	>25 mil (635 micron)

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 5891

FN10105



ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, using mild steel, grit blasted to a 3-4 mil profile, typical values are:

2,690 psi (18.54 MPa)	ambient cure
3,470 psi (23.92 MPa)	post cure
3,350 psi (23.10 MPa)	post cure and tested at 212°F (100°C)

Pull Off Adhesion

When tested in accordance with ASTM D4541/ ISO 4624, the pull off strength from grit blasted steel will be typically:

4,800 psi (33.09 MPa)	ambient cure
5,700 psi (39.30 MPa)	post cure

CATHODIC DISBONDMENT

When tested in accordance with ASTM G42 at 158°F (70°C) the disbondment diameter is typically 0.4 in (10.2mm).

CHEMICAL RESISTANCE

The material will demonstrate excellent resistance to a broad range of chemicals.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

COMPRESSIVE STRENGTH

When tested in accordance with ASTM D695, typical values obtained are:

13,800 psi (95.15 MPa)	ambient cure
20,000 psi (137.90 MPa)	post cure

EXPLOSIVE DECOMPRESSION

When tested to NACE TM 0185, using a seawater/hydrocarbon test fluid, the coating will exhibit no breakdown after a 21 day immersion period at 158°F(70°C) and 70 bar pressure followed by decompression over 15 minutes.

FLEXURAL STRENGTH

When tested to ASTM D790 typical values obtained are:

6,500 psi (44.82 MPa)	ambient cure
9,600 psi (66.19 MPa)	post cure

HARDNESS

Shore D

The Shore D hardness of the material when tested to ASTM D2240 is typically:

87	ambient cure
87	post cure

Koenig Pendulum

When tested to ISO 1522 the Koenig damping time of the coating will be typically:

85 seconds	ambient cure
142 seconds	post cure

HEAT RESISTANCE

Heat Distortion Temperature

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be:

124°F (51°C)	ambient cure
252°F (122°C)	post cure

Heat Resistance

Atlas Cell

When tested in accordance with NACE TM 0174 the coating will exhibit no rusting (ASTM D714 rating 10) or blistering (ASTM D610 rating 10) after 6 months immersion in water at 194°F (90°C).

Seawater immersion

When tested in accordance with ISO 2812, no blistering, rusting, cracking or delamination was observed after 6 months immersion in seawater at 104°F (40°C).

Steam-out Resistance

Once fully cured the coating will exhibit no blistering, cracking or delamination after 96 hours exposure to pressurised steam at 410°F (210°C).

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 446°F (230°C).

For many applications the product is suitable down to -40°F (-40°C).

IMPACT RESISTANCE

Izod Impact Strength

The Izod impact strength of the material when tested in accordance with ASTM D256 is typically:

Notched	Un-notched	
27 J/m	29 J/m	ambient cure
48 J/m	83 J/m	post cure

PRODUCT SPECIFICATION SHEET

BELZONA 5891

FN10105



THERMAL PROPERTIES

Low Temperature Thermal Shock

Coated steel panels will exhibit no blistering, cracking or delamination after multiple cycles of rapid cooling from 212°F to -76°F (100°C to -60°C).

Thermal Cycling

When tested in accordance with section 9 of NACE TM0304, the coating passed after 252 cycles between +140°F and -22°F (+60°C and -30°C).

THICK FILM CRACKING

When tested in accordance with Section 12 of NACE TM0104, the coating at three times recommended thickness, exhibited no cracking after 12 weeks immersion in seawater at 104°F (40°C).

SHELF LIFE

Separate Base and Solidifier components will have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

APPROVALS/ACCEPTANCES

The material has received recognition from organizations worldwide including:

USDA
WRAS

PRODUCT SPECIFICATION SHEET

BELZONA 5891

FN10105



WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 5891 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

